

## ABSTRACT OF THE DISCLOSURE

Cleaning solution is used to clean ceramic parts using the same. The cleaning solution includes about 5-30% by weight of fluoric salt, about 10-20% by weight of organic acid, about 30-50% by weight of organic solvent, and about 50% by weight of water. The ceramic parts may be portions of an etching apparatus on which plasma reaction by-products are adsorbed. Plasma reaction by-products are removed from the ceramic parts dipping the parts into the cleaning solution, followed by rinsing and heat treatment.